




P.T.B.- REFRACTAIRE-M

Refractory
mortar



Qualities

P.T.B.-REFRACTAIRE-M is a ready-to-use refractory mortar, that at the same time has faster bonding characteristics than a traditional mortar.



Use

P.T.B.-REFRACTAIRE-M is used for building and jointing brick chimneys, fireplaces, barbecues, chimney pots, etc.



Directions for use

Use always a substrate that is clean and if necessary moisten it. For masonry, P.T.B.-REFRACTAIRE-M is prepared with ± 15 to 20% water. For jointing P.T.B.-REFRACTAIRE-M is prepared with ± 10 to 15% water. After a few days of hardening, heating is applied gradually.



Packaging

P.T.B.-REFRACTAIRE-M is available in bags of 25 kg and pails of 5 kg. Every bag contains a polythylene inner bag that guarantees long-lasting conservation.



+30°

+5°

Refer to clause p. 2.



Mixing ratio	Consumption	Packaging
jointing: ± 10 to 15 % water brick work & cementation: ± 15 to 20% of water	jointing: ± 250 g/running meter cementations: ± 15 to 25 kg/m ²	5 (bucket) & 25 kg
Colours	Processing time	Application temperature
brown-grey	max. 45 min.	+ 5 till + 30 °C